

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): The use of the A method for inhibiting adhesion of a plastic to a mold, the method comprising:

providing a compound R<sub>n</sub><sup>1</sup>PO<sub>3</sub><sup>Θ</sup>(HN<sup>⊕</sup>-R<sub>3</sub><sup>2</sup>)<sub>m</sub> (I)

as a release agent during the cast polymerization of methyl methacrylate mixtures,

wherein:

R<sup>1</sup> = methyl, ethyl, propyl, isopropyl, butyl, isobutyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl;

R<sup>2</sup> = methyl, ethyl, propyl, isopropyl, butyl;

n = 1 or 2;

m = 2 or 1; and n + m = 3.

Claim 2 (Currently Amended): The use of The method of claim 1, wherein the use of the compound of the formula I is present in amounts an amount of 0.01 - 5% by weight, based on the weight of the polymerizable monomers or monomer mixture composed of (meth)acrylates and other copolymerizable monomers, as the release agent.

Claim 3 (Currently Amended): The use of The method of claim 1, wherein the release agent agents as claimed in claim 1 or 2 is useful for the production of plastics moldings composed of (meth)acrylates and other copolymerizable monomers.

Claim 4 (Currently Amended): A plastics molding composed of (meth)acrylates and other copolymerizable monomers, comprising: compounds a compound of the formula I

R<sub>n</sub><sup>1</sup>PO<sub>3</sub><sup>Θ</sup>(HN<sup>⊕</sup>-R<sub>3</sub><sup>2</sup>)<sub>m</sub>(I)

as a release agent during the cast polymerization of methyl methacrylate mixtures,

wherein:

R<sup>1</sup> = methyl, ethyl, propyl, isopropyl, butyl, isobutyl, pentyl, hexyl, heptyl, octyl,  
nonyl, decyl, undecyl, dodecyl;

R<sup>2</sup> = methyl, ethyl, propyl, isopropyl, butyl;

n = 1 or 2;

m = 2 or 1; and

n + m = 3.